



FRANCHISSEMENT RÉGLEMENTÉ



Construction

face-film	PVC	
thickness	75 µm	
adhesive	acrylic pressure adhesive	square quantity : 20g/m ²
release liner	PE-coated silicon cardboard	square weight : 144 g/m ²

Characteristics

adhesive strength (ASTMD-903)	immediately after 1 week	6.3N/25 mm 10N/25 mm
dimensional stability	applied onto aluminium after 48 hours stored at 70°C (25x25 cm)	max. -0.45%
chemise resistance	In a preece test of 24 hours the applied film is resistant to most petroleum based oils, greases and aliphatic solvents, mild acids, alhaline and salts.	
light proofness	DIN 53 388	non-fade grade : 7-8 (wool-scale)
combustibility	stuck on aluminium, the film is self-extinguishing	
temperature	application temperature service temperature range	min 15°C -30°C up to +80°C
minimum durability	7 years outdoors, with vertical exposure, in middle-European climate.	